

Durethan® B40FD

PA6

Film Extrusion, Unreinforced, Extrusion, Food Contact Quality, High Viscosity

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	2800 / 800	MPa	ISO 527-1/-2
Nominal strain at break	20 / >50	%	ISO 527-1/-2
Yield stress	75 / 35	MPa	ISO 527-1/-2
Yield strain	4 / 25	%	ISO 527-1/-2
Flexural modulus	2600 / 700	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	5 / 50	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	5 / 5	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	50 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	150 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.8 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 0.75 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Oxygen index	24 / *	%	ISO 4589-1/-2

Property Data

Durethan® B40FD

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
OTHER PROPERTIES	DRY / COND		
Water absorption	10 / *	%	Sim. to ISO 62
Humidity absorption	3 / *	%	Sim. to ISO 62
Density	1140 / –	kg/m³	ISO 1183