

Durethan® BC304H3.0

PA6—I

Injection Molding, Unreinforced, Heat Stabilized, Improved Impact

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	1800 / 800	MPa	ISO 527-1/-2
Nominal strain at break	>50 / >50	%	ISO 527-1/-2
Yield stress	45 / 35	MPa	ISO 527-1/-2
Yield strain	4.5 / 30	%	ISO 527-1/-2
Flexural modulus	1600 / 700	MPa	ISO 178
Flexural strength	60 / 30	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	85 / 120	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	20 / 20	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	70 / 100	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	50 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	90 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	1.5 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.6 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Oxygen index	21 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	650 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2 / -	mm	IEC 60695-2-12

Durethan® BC304H3.0

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES			
	DRY / COND		
Relative permittivity (100Hz)	3.3 / 11	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3 / 3.5	–	IEC 62631–2–1
Dissipation factor (100 Hz)	70 / 1750	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	150 / 900	E–4	IEC 62631–2–1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631–3–1
Surface resistivity	* / 1E14	Ohm	IEC 62631–3–2
Electric strength	35 / 35	kV/mm	IEC 60243–1
Comparative tracking index	600 / –	V	IEC 60112
OTHER PROPERTIES			
	DRY / COND		
Water absorption	7.5 / *	%	Sim. to ISO 62
Humidity absorption	2.2 / *	%	Sim. to ISO 62
Density	1060 / –	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS			
	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	80–90	°C	