

Durethan® BKV130H2.0EF

PA6-I-GF30

30% Glass Reinforced, Injection Molding, Improved flow, Improved Impact

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.25 / *	%	ISO 294-4
Molding shrinkage (normal)	0.7 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	9000 / –	MPa	ISO 527-1/-2
Flexural modulus	8300 / –	MPa	ISO 178
Flexural strength	235 / –	MPa	ISO 178
Charpy impact strength (+23°C)	90 / 90	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	85 / 85	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 20	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	10 / 10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	13 / 20	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	206 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	150 / *	°C	ISO 75-1/-2
OTHER PROPERTIES			
	DRY / COND		
Humidity absorption	2.13 / *	%	Sim. to ISO 62
Density	1340 / –	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS **VALUE**

Property Data

Durethan® BKV130H2.0EF

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	80–100	°C	