

Durethan® BKV15 DUS008

PA6—GF15

15% Glass Reinforced, Injection Molding

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.35 / *	%	ISO 294-4
Molding shrinkage (normal)	0.59 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	6500 / 3100	MPa	ISO 527-1/-2
Stress at break	130 / 65	MPa	ISO 527-1/-2
Strain at break	3 / 12	%	ISO 527-1/-2
Flexural modulus	5500 / 3100	MPa	ISO 178
Flexural strength	205 / 110	MPa	ISO 178
Charpy impact strength (+23°C)	50 / 100	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	45 / 45	kJ/m²	ISO 179/1eU
Izod notched impact strength (+23°C)	<10 / 10	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	195 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10

Property Data

Durethan® BKV15 DUS008

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Burning Behav. at 0.75 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10

OTHER PROPERTIES	DRY / COND		
Density	1230 / –	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2-6	h	
Melt temperature (Tmin – Tmax)	260-290	°C	
Mold temperature	80-100	°C	