

Durethan® BKV15GH2.0

PA6–GF15

15% Glass Reinforced, Injection Molding, Heat Stabilized, Excellent Surface Properties

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	6300 / 4000	MPa	ISO 527-1/-2
Stress at break	120 / 70	MPa	ISO 527-1/-2
Strain at break	3 / 11	%	ISO 527-1/-2
Flexural modulus	5700 / 3500	MPa	ISO 178
Flexural strength	185 / 125	MPa	ISO 178
Tensile modulus (200°C)	1280	MPa	ISO 527-1/-2
Charpy impact strength (+23°C)	30 / 40	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	35 / 35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	<10 / <10	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	<10 / <10	kJ/m ²	ISO 179/1eA
Izod notched impact strength (-40°C)	<10 / <10	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	218 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	180 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Oxygen index	23 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	650 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2 / -	mm	IEC 60695-2-12

Property Data

Durethan® BKV15GH2.0

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>ELECTRICAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Relative permittivity (100Hz)	4.1 / 10	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3.7 / 4.3	–	IEC 62631–2–1
Dissipation factor (100 Hz)	80 / 2200	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	180 / 700	E–4	IEC 62631–2–1
Volume resistivity	1E11 / 1E9	Ohm*m	IEC 62631–3–1
Surface resistivity	* / 1E13	Ohm	IEC 62631–3–2
Electric strength	30 / 30	kV/mm	IEC 60243–1
Comparative tracking index	375 / –	V	IEC 60112
<i>OTHER PROPERTIES</i>			
	<i>DRY / COND</i>		
Water absorption	7.8 / *	%	Sim. to ISO 62
Humidity absorption	2.6 / *	%	Sim. to ISO 62
Density	1240 / –	kg/m ³	ISO 1183
<i>MATERIAL SPECIFIC PROPERTIES</i>			
	<i>DRY / COND</i>		
Viscosity number	138 / *	cm ³ /g	ISO 307, 1157, 1628
<i>PROCESSING RECOMMENDATIONS</i>			
	<i>VALUE</i>		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–290	°C	
Mold temperature	80–100	°C	