

Durethan® BKV30GW1 DUS037

PA6—GF30

30% Glass Reinforced, Injection Molding, Heat Stabilized

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.2 / *	%	ISO 294-4
Molding shrinkage (normal)	0.6 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	9900 / 6600	MPa	ISO 527-1/-2
Stress at break	180 / 106	MPa	ISO 527-1/-2
Strain at break	2.7 / 6.1	%	ISO 527-1/-2
Flexural modulus	8700 / 6300	MPa	ISO 178
Flexural strength	270 / 177	MPa	ISO 178
Charpy impact strength (+23°C)	60 / 65	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	50 / 40	kJ/m²	ISO 179/1eU
Izod notched impact strength (+23°C)	10 / 10	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	219 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8 / *	E-4/°C	ISO 11359-1/-2
OTHER PROPERTIES			
	DRY / COND		
Water absorption	6.4 / *	%	Sim. to ISO 62
Humidity absorption	2 / *	%	Sim. to ISO 62

Durethan® BKV30GW1 DUS037

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Density	1360 / –	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	270–290	°C	
Mold temperature	80–120	°C	