

Durethan® BKV30H2.0EF DUS074

PA6—GF30

30% Glass Reinforced, Injection Molding, Heat Stabilized, Improved flow

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.25 / *	%	ISO 294-4
Molding shrinkage (normal)	0.65 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	8400 / 4800	MPa	ISO 527-1/-2
Stress at break	160 / 85	MPa	ISO 527-1/-2
Strain at break	3 / 5.5	%	ISO 527-1/-2
Flexural modulus	8200 / 4500	MPa	ISO 178
Flexural strength	230 / 135	MPa	ISO 178
Tensile modulus (200°C)	2320	MPa	ISO 527-1/-2
Charpy impact strength (+23°C)	65 / 80	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	55 / 40	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / 18	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	<10 / <10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	10 / 18	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	212 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	195 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2

Durethan® BKV30H2.0EF DUS074

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
OTHER PROPERTIES	DRY / COND		
Density	1350 / –	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	80–120	°C	