

Durethan® BKV35CXH2.0

PA6—GF35

35% Glass Reinforced, Injection Molding, Foam Applications, Heat Stabilized

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.2 / *	%	ISO 294-4
Molding shrinkage (normal)	0.65 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	10500 / 6500	MPa	ISO 527-1/-2
Stress at break	180 / 110	MPa	ISO 527-1/-2
Strain at break	3 / 5.5	%	ISO 527-1/-2
Flexural modulus	10000 / 6000	MPa	ISO 178
Flexural strength	270 / 175	MPa	ISO 178
Charpy impact strength (+23°C)	85 / 85	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	65 / 60	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	12 / 18	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 10	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	12 / 18	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	205 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10

Durethan® BKV35CXH2.0

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
OTHER PROPERTIES	DRY / COND		
Density	1410 / –	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250–290	°C	
Mold temperature	80–120	°C	