

Durethan® BKV50H3.0EF 703163

PA6—GF50

50% Glass Reinforced, Injection Molding, Heat Stabilized, Improved flow

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	0.7 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	16700 / 11000	MPa	ISO 527-1/-2
Stress at break	220 / 140	MPa	ISO 527-1/-2
Strain at break	2.5 / 4	%	ISO 527-1/-2
Flexural modulus	17000 / 11700	MPa	ISO 178
Flexural strength	345 / 225	MPa	ISO 178
Charpy impact strength (+23°C)	90 / 90	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	90 / 80	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	15 / 20	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	15 / 15	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	15 / 20	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	212 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
OTHER PROPERTIES			
	DRY / COND		
Density	1600 / -	kg/m³	ISO 1183

Durethan® BKV50H3.0EF 703163

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.03–0.12	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	270–290	°C	
Mold temperature	80–120	°C	