

Durethan® BLUEBKV60EF DUS097

PA6—GF60

60% Glass Reinforced, Injection Molding, Heat Stabilized, Improved flow, Recycled Content

Sustainability

Bio-based
 Mass balanced
 Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	0.6 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	19400 / 12000	MPa	ISO 527-1/-2
Stress at break	230 / 150	MPa	ISO 527-1/-2
Strain at break	2.5 / 3.5	%	ISO 527-1/-2
Flexural modulus	18000 / 12500	MPa	ISO 178
Flexural strength	375 / 240	MPa	ISO 178
Charpy impact strength (+23°C)	95 / 95	kJ/m²	ISO 179/1eU
Charpy impact strength (-30°C)	95 / 95	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	17 / 24	kJ/m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	17 / -	kJ/m²	ISO 179/1eA
Izod notched impact strength (+23°C)	18 / 29	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	221 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	213 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2

Durethan® BLUEBKV60EF DUS097

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Coeff. of linear therm. expansion (parallel)	0.1 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.8 / *	E-4/°C	ISO 11359-1/-2
ELECTRICAL PROPERTIES		DRY / COND	
Comparative tracking index	600 / –	V	IEC 60112
OTHER PROPERTIES		DRY / COND	
Water absorption	3.75 / *	%	Sim. to ISO 62
Humidity absorption	1.18 / *	%	Sim. to ISO 62
Density	1700 / –	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS		VALUE	
Drying temperature dry air dryer	80	°C	
Drying time dry air dryer	2–6	h	
Residual moisture content	0.05–0.15	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	270–290	°C	
Mold temperature	80–120	°C	