

Novamid[®] 1013G45 1 NA

PA6—GF45

45% Glass Reinforced, Injection Molding

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	DRY / COND		
Molding shrinkage (parallel)	0.2 / *	%	ISO 294-4
Molding shrinkage (normal)	0.8 / *	%	ISO 294-4
MECHANICAL PROPERTIES	DRY / COND		
Tensile modulus	13600 / 9000	MPa	ISO 527-1/-2
Stress at break	220 / 150	MPa	ISO 527-1/-2
Strain at break	3 / 5	%	ISO 527-1/-2
Flexural modulus	13600 / 9000	MPa	ISO 178
Flexural strength	355 / 250	MPa	ISO 178
Charpy impact strength (+23°C)	110 / 120	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	18 / 27	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	209 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	5 / –	–	IEC 62631-2-1
Relative permittivity (1 MHz)	4 / –	–	IEC 62631-2-1
Dissipation factor (100 Hz)	280 / –	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	240 / –	E-4	IEC 62631-2-1
Volume resistivity	2E12 / –	Ohm*m	IEC 62631-3-1

Property Data

Novamid® 1013G45 1 NA

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Surface resistivity	– / 3E13	Ohm	IEC 62631–3–2
Electric strength	27 / –	kV/mm	IEC 60243–1
Comparative tracking index	400 / –	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1490 / –	kg/m³	ISO 1183