

# Novamid<sup>®</sup> 1015B

## PA6

Low Viscosity, Injection Molding

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b>THERMAL PROPERTIES</b>			
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
<b>OTHER PROPERTIES</b>			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m <sup>3</sup>	ISO 1183
<b>MATERIAL SPECIFIC PROPERTIES</b>			
Viscosity number	150 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

# Novamid<sup>®</sup> 1015B

Viscosity–shear rate

