

Novamid[®] 1015GT30 BK37

PA6-I-GF30

Improved Impact, Glass Reinforced

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>RHEOLOGICAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Molding shrinkage [parallel]	0.5 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.4 / *	%	Sim. to ISO 294-4
<i>MECHANICAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Strain at break	7 / -	%	ISO 527-1/-2
<i>THERMAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
<i>OTHER PROPERTIES</i>			
	<i>DRY / COND</i>		
Water absorption	1.8 / *	%	Sim. to ISO 62
Density	1330 / -	kg/m ³	ISO 1183