

# Novamid<sup>®</sup> 1017-AH1 (N-X174)

## PA6

Medium Viscosity, Extrusion Grade, Heat Stabilized, UV Stabilized

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b>MATERIAL SPECIFIC PROPERTIES</b>			
	<i>VALUE</i>		
Viscosity number	168	cm <sup>3</sup> /g	ISO 307, 1157, 1628
RSV formic acid, 1g/100ml	2.7	–	Envalior Method
Melt Viscosity (260 °C)	410	Pa s	Envalior Method, 260 °C
Density	1130	kg/m <sup>3</sup>	ISO 1183
<b>THERMAL PROPERTIES</b>			
	<i>VALUE</i>		
Coeff. of linear therm. expansion (parallel)	0.9	E-4/°C	ISO 11359-1/-2
Spec. heat capacity	1550	J/(kg K)	–
Average spec. heat capacity 20–150 °C	2250	J/(kg K)	
<b>MECHANICAL PROPERTIES (FILM)</b>			
	<i>VALUE</i>		
Modulus of elasticity	460	MPa	Envalior Method, 50 mm/min
Stress at yield, parallel	32	MPa	ISO 527-3
Maximum stress, parallel	80	MPa	ISO 527-3
Maximum strain, parallel	350	%	ISO 527-3
Trouser Tear resistance, parallel	32	–	ISO 6383-1
Puncture resistance	1150	J/m	Envalior Method
Static coefficient of friction	1.5	–	ISO 8295
Dynamic coefficient of friction	1.2	–	ISO 8295
<b>OTHER PROPERTIES (FILM)</b>			
	<i>VALUE</i>		

## Property Data

# Novamid® 1017-AH1 (N-X174)

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Transparency/Clarity	83	%	Envalior Method
Oxygen transmission rate at 23°C/0%r.h.	26	cm <sup>3</sup> /(m <sup>2</sup> *d*bar)	DIS 15105-1/-2
Oxygen transmission rate at 23°C/85%r.h.	38	cm <sup>3</sup> /(m <sup>2</sup> *d*bar)	DIS 15105-1/-2
Water Vapor Transmission Rate at 23°C/85%r.h.	35	g/(m <sup>2</sup> *d)	DIS 15106-1/-3

### TEST SPECIMEN PRODUCTION (FILM)

### VALUE

Type of extrusion	cast	—	—
Thickness of specimen	0.05	mm	—
Extruder temperature	270	°C	
Die temperature	270	°C	
Chill Roll Temperature	110	°C	

### Viscosity—shear rate

