

Novamid[®] 1022CZ3

PA6

Extrusion Grade, Film Extrusion, Lubricated, Antiblock, Food Contact Quality

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / –	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	194 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid® 1022CZ3

Viscosity–shear rate

