

Novamid[®] ST220 NAT

PA6—I

Impact Modified, Injection Molding, Medium Viscosity

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	DRY / COND		
Molding shrinkage [parallel]	1.5 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	2 / *	%	Sim. to ISO 294-4
MECHANICAL PROPERTIES	DRY / COND		
Tensile modulus	2100 / 630	MPa	ISO 527-1/-2
Yield stress	50 / 30	MPa	ISO 527-1/-2
Yield strain	4.4 / 21.6	%	ISO 527-1/-2
Nominal strain at break	35 / >50	%	ISO 527-1/-2
Flexural modulus	2000 / 650	MPa	ISO 178
Flexural strength	76 / 30	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	85 / N	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	53 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	87 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.9 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1 / *	E-4/°C	ISO 11359-1/-2
ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	4 / —	—	IEC 62631-2-1
Relative permittivity (1 MHz)	3 / —	—	IEC 62631-2-1

Property Data

Novamid® ST220 NAT

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Dissipation factor (100 Hz)	100 / –	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	180 / –	E–4	IEC 62631–2–1
Volume resistivity	9E12 / –	Ohm*m	IEC 62631–3–1
Surface resistivity	– / 3E13	Ohm	IEC 62631–3–2
Electric strength	29 / –	kV/mm	IEC 60243–1
Comparative tracking index	600 / –	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Humidity absorption	2.2 / *	%	Sim. to ISO 62
Density	1070 / –	kg/m³	ISO 1183