

Akulon[®] S240-C

PA66

Food Contact Quality, High Viscosity

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
MATERIAL SPECIFIC PROPERTIES			
	<i>DRY / COND</i>		
Viscosity number	280 / *	cm ³ /g	ISO 307, 1157, 1628
Density	1140 / -	kg/m ³	ISO 1183
THERMAL PROPERTIES			
	<i>DRY / COND</i>		
Coeff. of linear therm. expansion (parallel)	0.9 / *	E-4/°C	ISO 11359-1/-2
OTHER PROPERTIES (FILM)			
	<i>VALUE</i>		
Oxygen transmission rate at 23°C/0%r.h.	27	cm ³ /(m ² *d*bar)	DIS 15105-1/-2
Oxygen transmission rate at 23°C/85%r.h.	41	cm ³ /(m ² *d*bar)	DIS 15105-1/-2
Water Vapor Transmission Rate at 23°C/85%r.h.	24	g/(m ² *d)	DIS 15106-1/-3
TEST SPECIMEN PRODUCTION (FILM)			
	<i>VALUE</i>		
Type of extrusion	cast	-	-
Thickness of specimen	0.06	mm	-
Chill Roll Temperature	100	°C	

Akulon[®] S240-C

Viscosity-shear rate

