

Novamid[®] 3021GH30 NAT

PA66–GF30

30% Glass Reinforced, Heat Stabilized

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>RHEOLOGICAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Molding shrinkage [parallel]	0.4 / *	%	Sim. to ISO 294–4
Molding shrinkage [normal]	1.3 / *	%	Sim. to ISO 294–4
<i>MECHANICAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Tensile modulus	9700 / 6500	MPa	ISO 527–1/–2
Stress at break	170 / 130	MPa	ISO 527–1/–2
Strain at break	2.6 / 4	%	ISO 527–1/–2
Flexural modulus	8300 / 6500	MPa	ISO 178
Flexural strength	267 / 200	MPa	ISO 178
Charpy impact strength (+23°C)	80 / 110	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / 13	kJ/m ²	ISO 179/1eA
<i>THERMAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	244 / *	°C	ISO 75–1/–2
<i>ELECTRICAL PROPERTIES</i>			
	<i>DRY / COND</i>		
Relative permittivity (1 MHz)	4 / –	–	IEC 62631–2–1
Dissipation factor (1 MHz)	190 / –	E–4	IEC 62631–2–1
Volume resistivity	>1E13 / –	Ohm*m	IEC 62631–3–1
Surface resistivity	– / 4E14	Ohm	IEC 62631–3–2
Electric strength	26 / –	kV/mm	IEC 60243–1
Comparative tracking index	550 / –	V	IEC 60112

Property Data

Novamid[®] 3021GH30 NAT

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
OTHER PROPERTIES			
Humidity absorption	1.7 / *	%	Sim. to ISO 62
Density	1370 / –	kg/m ³	ISO 1183