

Novamid[®] 2020A-8

PA6/66

Extrusion, Monofilament Grade, Highly lubricated

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / –	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	183 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid® 2020A-8

Viscosity–shear rate

