

Novamid[®] 2020J

PA6/66

Extrusion, Medium/High Viscosity, Neat resin, Food Contact Quality

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
THERMAL PROPERTIES			
	<i>DRY / COND</i>		
Melting temperature (10°C/min)	200 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
	<i>DRY / COND</i>		
Water absorption	13 / *	%	Sim. to ISO 62
Humidity absorption	3.5 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
	<i>DRY / COND</i>		
Viscosity number	183 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid[®] 2020J

Viscosity–shear rate

