

Novamid[®] 2320A

PA6/66

Extrusion, Monofilament Grade, Highly lubricated

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
THERMAL PROPERTIES			
Melting temperature (10°C/min)	215 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
Viscosity number	183 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid[®] 2320A

Viscosity–shear rate

