

Novamid[®] 2420A

PA6/66

Extrusion, Monofilament Grade, Highly lubricated

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES	DRY / COND		
Humidity absorption	3.5 / *	%	Sim. to ISO 62
Density	1140 / –	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES	DRY / COND		
Viscosity number	183 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid® 2420A

Viscosity–shear rate

