

# Novamid<sup>®</sup> 2430A

## PA6/66

Extrusion Grade, Monofilament Grade, Highly lubricated, High Viscosity

Ideal for high tenacity & high transparency fishing monofilament extrusion.  
 High viscosity and high 66 content for larger diameter filament.

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b><i>THERMAL PROPERTIES</i></b>			
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
<b><i>OTHER PROPERTIES</i></b>			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m <sup>3</sup>	ISO 1183
<b><i>MATERIAL SPECIFIC PROPERTIES</i></b>			
Viscosity number	246 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

# Novamid<sup>®</sup> 2430A

Viscosity–shear rate

