

Novamid[®] 2430A3 (N-X158)

PA6/66

Extrusion Grade, Monofilament Grade, Highly lubricated, Improved Processing, High Viscosity

Monofilament

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>THERMAL PROPERTIES</i>			
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
<i>OTHER PROPERTIES</i>			
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
<i>MATERIAL SPECIFIC PROPERTIES</i>			
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628

Property Data

Novamid® 2430A3 (N-X158)

Viscosity–shear rate

