

Novamid[®] 2430J

PA6/66

Film Extrusion, Extrusion, Extrusion Grade, Food Contact Quality

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
THERMAL PROPERTIES			
Melting temperature (10°C/min)	193 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Humidity absorption	3.5 / *	%	Sim. to ISO 62
Density	1140 / -	kg/m ³	ISO 1183
MATERIAL SPECIFIC PROPERTIES			
Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628

Novamid[®] 2430J

Viscosity–shear rate

