

# Arnite<sup>®</sup> T04 200

## PBT

Low Viscosity

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b><i>RHEOLOGICAL PROPERTIES</i></b>			
	<i>VALUE</i>		
Melt volume–flow rate	75	cm <sup>3</sup> /10min	ISO 1133
Temperature	250	°C	ISO 1133
Load	2.16	kg	ISO 1133
<b><i>THERMAL PROPERTIES</i></b>			
	<i>VALUE</i>		
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
<b><i>OTHER PROPERTIES</i></b>			
	<i>VALUE</i>		
Water absorption	0.45	%	Sim. to ISO 62
Humidity absorption	0.18	%	Sim. to ISO 62
Density	1300	kg/m <sup>3</sup>	ISO 1183

Property Data

# Arnite® T04 200

Viscosity–shear rate

