

Pocan[®] B1305 B–MB

PBT

Injection Molding, Unreinforced, General purpose

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>RHEOLOGICAL PROPERTIES</i>			
	<i>VALUE</i>		
Melt volume–flow rate	47	cm ³ /10min	ISO 1133
Temperature	250	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	2	%	ISO 294–4
Molding shrinkage (parallel)	2	%	ISO 294–4
<i>MECHANICAL PROPERTIES</i>			
	<i>VALUE</i>		
Tensile modulus	2800	MPa	ISO 527–1/–2
Yield stress	60	MPa	ISO 527–1/–2
Yield strain	9	%	ISO 527–1/–2
Flexural modulus	2700	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Flexural strain at flexural strength	6	%	ISO 178–A
Charpy impact strength (+23°C)	180	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	150	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	2.8	kJ/m ²	ISO 179/1eA
Izod impact strength (+23°C)	125	kJ/m ²	ISO 180/1U
Izod impact strength (–30°C)	90	kJ/m ²	ISO 180–1U
<i>THERMAL PROPERTIES</i>			
	<i>VALUE</i>		
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	65	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	155	°C	ISO 75–1/–2

Property Data

Pocan[®] B1305 B–MB

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Coeff. of linear therm. expansion (parallel)	1.1	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.1	E-4/°C	ISO 11359-1/-2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
Oxygen index	24	%	ISO 4589-1/-2
Glow Wire Flammability Index GWFI	750	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2	mm	IEC 60695-2-12

<i>ELECTRICAL PROPERTIES</i>	<i>VALUE</i>		
Relative permittivity (100Hz)	3.4	–	IEC 62631-2-1
Relative permittivity (1 MHz)	3.2	–	IEC 62631-2-1
Dissipation factor (100 Hz)	15	E-4	IEC 62631-2-1
Dissipation factor (1 MHz)	190	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	600	V	IEC 60112
Comparative tracking index (PLC)	0	class	UL 746A

<i>OTHER PROPERTIES</i>	<i>VALUE</i>		
Water absorption	0.5	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1310	kg/m ³	ISO 1183

<i>PROCESSING RECOMMENDATIONS</i>	<i>VALUE</i>
-----------------------------------	--------------

Property Data

Pocan[®] B1305 B–MB

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250–270	°C	
Mold temperature	80–100	°C	

Viscosity–shear rate

