

Pocan[®] B3225XF

PBT–GF20

20% Glass Reinforced, Injection Molding, Improved flow, Improved Impact

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume–flow rate	35	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	1.1	%	ISO 294–4
Molding shrinkage (parallel)	0.5	%	ISO 294–4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	6500	MPa	ISO 527–1/–2
Stress at break	105	MPa	ISO 527–1/–2
Strain at break	3.5	%	ISO 527–1/–2
Flexural modulus	6100	MPa	ISO 178
Flexural strength	165	MPa	ISO 178
Flexural strain at flexural strength	3.7	%	ISO 178–A
Charpy impact strength (+23°C)	60	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8.3	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	7.2	kJ/m ²	ISO 179/1eA
Izod impact strength (+23°C)	50	kJ/m ²	ISO 180/1U
Izod impact strength (–30°C)	40	kJ/m ²	ISO 180–1U
THERMAL PROPERTIES			
	VALUE		
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	200	°C	ISO 75–1/–2

Property Data

Pocan® B3225XF

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.3	E-4/°C	ISO 11359-1/-2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	750	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	2	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	2	mm	IEC 60695-2-13

ELECTRICAL PROPERTIES	VALUE		
Comparative tracking index	400	V	IEC 60112

OTHER PROPERTIES	VALUE		
Water absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1400	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4-8	h	
Residual moisture content	0.00-0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250-270	°C	
Mold temperature	80-100	°C	

Pocan[®] B3225XF

Viscosity–shear rate

