

# Pocan<sup>®</sup> B3233HRE

## PBT–GF30

30% Glass Reinforced, Injection Molding, Hydrolysis resistant, Improved flow

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b>RHEOLOGICAL PROPERTIES</b>			
	<b>VALUE</b>		
Melt volume–flow rate	15	cm <sup>3</sup> /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	1	%	ISO 294–4
Molding shrinkage (parallel)	0.4	%	ISO 294–4
<b>MECHANICAL PROPERTIES</b>			
	<b>VALUE</b>		
Tensile modulus	9700	MPa	ISO 527–1/–2
Stress at break	120	MPa	ISO 527–1/–2
Strain at break	2.6	%	ISO 527–1/–2
Flexural modulus	9200	MPa	ISO 178
Flexural strength	190	MPa	ISO 178
Flexural strain at flexural strength	2.9	%	ISO 178–A
Charpy impact strength (+23°C)	60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (–30°C)	60	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL PROPERTIES</b>			
	<b>VALUE</b>		
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	202	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.2	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	1.3	E–4/°C	ISO 11359–1/–2

## Property Data

# Pocan<sup>®</sup> B3233HRE

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b><i>ELECTRICAL PROPERTIES</i></b>			
Comparative tracking index	600	V	IEC 60112
<b><i>OTHER PROPERTIES</i></b>			
Density	1530	kg/m <sup>3</sup>	ISO 1183
<b><i>PROCESSING RECOMMENDATIONS</i></b>			
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250–270	°C	
Mold temperature	80–100	°C	