

Pocan[®] B3235LT

PBT–GF30

30% Glass Reinforced, Injection Molding, Laser Transparent Black

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume–flow rate	20	cm ³ /10min	ISO 1133
Temperature	270	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	0.8	%	ISO 294–4
Molding shrinkage (parallel)	0.3	%	ISO 294–4
MECHANICAL PROPERTIES		VALUE	
Tensile modulus	10000	MPa	ISO 527–1/–2
Stress at break	140	MPa	ISO 527–1/–2
Strain at break	2.8	%	ISO 527–1/–2
Flexural modulus	9500	MPa	ISO 178
Flexural strength	225	MPa	ISO 178
Flexural strain at flexural strength	3.2	%	ISO 178–A
Charpy impact strength (+23°C)	62	kJ/m ²	ISO 179/1eU
Izod impact strength (+23°C)	54	kJ/m ²	ISO 180/1U
THERMAL PROPERTIES		VALUE	
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	195	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	215	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.2	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	1	E–4/°C	ISO 11359–1/–2

Property Data

Pocan[®] B3235LT

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES			
Comparative tracking index	300	V	IEC 60112
OTHER PROPERTIES			
Density	1520	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS			
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	60–80	°C	