

Pocan[®] C1506

(PBT+PC)–I

Injection Molding, Unreinforced, Excellent Surface Properties, Low Warpage

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume–flow rate	30	cm ³ /10min	ISO 1133
Temperature	270	°C	ISO 1133
Load	5	kg	ISO 1133
Molding shrinkage (normal)	0.8	%	ISO 294–4
Molding shrinkage (parallel)	0.8	%	ISO 294–4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	2400	MPa	ISO 527–1/–2
Yield stress	60	MPa	ISO 527–1/–2
Yield strain	4.8	%	ISO 527–1/–2
Flexural modulus	2400	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Flexural strain at flexural strength	6	%	ISO 178–A
Charpy notched impact strength (+23°C)	57	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	13	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	VALUE		
Melting temperature (10°C/min)	220	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	100	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	105	°C	ISO 75–1/–2
OTHER PROPERTIES			
	VALUE		
Density	1220	kg/m ³	ISO 1183

Property Data

Pocan[®] C1506

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>PROCESSING RECOMMENDATIONS</i>			
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Melt temperature (Tmin – Tmax)	250–270	°C	
Mold temperature	80–100	°C	
admissible residence time at Tmax	<5	min	