

Pocan[®] C5211

(PBT+PC)—I—MD10

10% Mineral Reinforced, Injection Molding, Improved Impact, Excellent Surface Properties, Low Warpage

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume–flow rate	45	cm ³ /10min	ISO 1133
Temperature	270	°C	ISO 1133
Load	5	kg	ISO 1133
Molding shrinkage (normal)	0.7	%	ISO 294–4
Molding shrinkage (parallel)	0.7	%	ISO 294–4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	3300	MPa	ISO 527–1/–2
Stress at break	50	MPa	ISO 527–1/–2
Strain at break	12	%	ISO 527–1/–2
Flexural modulus	3550	MPa	ISO 178
Flexural strength	95	MPa	ISO 178
Flexural strain at flexural strength	5.2	%	ISO 178–A
Charpy impact strength (+23°C)	200	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	150	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	7	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	7	kJ/m ²	ISO 179/1eA
Izod impact strength (+23°C)	140	kJ/m ²	ISO 180/1U
Izod impact strength (–30°C)	100	kJ/m ²	ISO 180–1U
THERMAL PROPERTIES			
	VALUE		
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	100	°C	ISO 75–1/–2

Property Data

Pocan[®] C5211

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Temp. of deflection under load (0.45 MPa)	120	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.8	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7	E-4/°C	ISO 11359-1/-2

OTHER PROPERTIES	VALUE		
Density	1290	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4-8	h	
Residual moisture content	0.00-0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250-270	°C	
Mold temperature	80-100	°C	