

Pocan[®] ECOB3233HR

PBT–GF30

30% Glass Reinforced, Injection Molding, Hydrolysis resistant, Improved flow, Recycled Content

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Melt volume–flow rate	15	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	1	%	ISO 294–4
Molding shrinkage (parallel)	0.3	%	ISO 294–4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	9600	MPa	ISO 527–1/–2
Stress at break	125	MPa	ISO 527–1/–2
Strain at break	2.9	%	ISO 527–1/–2
Flexural modulus	9100	MPa	ISO 178
Flexural strength	200	MPa	ISO 178
Flexural strain at flexural strength	3.2	%	ISO 178–A
Charpy impact strength (+23°C)	65	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	55	kJ/m ²	ISO 179/1eU
Izod impact strength (+23°C)	55	kJ/m ²	ISO 180/1U
Izod impact strength (–30°C)	55	kJ/m ²	ISO 180–1U
THERMAL PROPERTIES			
	VALUE		
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75–1/–2

Property Data

Pocan® ECOB3233HR

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Coeff. of linear therm. expansion (parallel)	0.3	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.3	E-4/°C	ISO 11359-1/-2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	800	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.8	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	800	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	1.5	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	825	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	0.8	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	825	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	1.5	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	825	°C	IEC 60695-2-13
GWIT (Thickness (3) tested)	3	mm	IEC 60695-2-13

ELECTRICAL PROPERTIES	VALUE		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	35	kV/mm	IEC 60243-1
Comparative tracking index	475	V	IEC 60112
Comparative tracking index (PLC)	1	class	UL 746A

OTHER PROPERTIES	VALUE		
Density	1480	kg/m³	ISO 1183

Property Data

Pocan[®] ECOB3233HR

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	250–270	°C	
Mold temperature	80–100	°C	