

Pocan[®] KU1–7625LT

(PBT+PC)–GF20

20% Glass Reinforced, Injection Molding, Excellent Surface Properties, Laser Transparent Black, Low Warpage

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Melt volume–flow rate	40	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	5	kg	ISO 1133
MECHANICAL PROPERTIES	VALUE		
Tensile modulus	5100	MPa	ISO 527–1/–2
Stress at break	75	MPa	ISO 527–1/–2
Strain at break	4	%	ISO 527–1/–2
Flexural strain at flexural strength	4.5	%	ISO 178–A
Charpy impact strength (+23°C)	35	kJ/m ²	ISO 179/1eU
THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	225	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	110	°C	ISO 75–1/–2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	0.75	mm	IEC 60695–11–10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	1.5	mm	IEC 60695–11–10
OTHER PROPERTIES	VALUE		
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1400	kg/m ³	ISO 1183

Property Data

Pocan[®] KU1–7625LT

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
PROCESSING RECOMMENDATIONS	VALUE		
Melt temperature (Tmin – Tmax)	250–270	°C	
Mold temperature	70–100	°C	