

Pocan[®] ECOT7142

(PET+PBT)–(GF+MX)40

40% Glass/Mineral Reinforced, Injection Molding, Recycled Content

Sustainability

Mass balanced
Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Molding shrinkage (normal)	0.8	%	ISO 294–4
Molding shrinkage (parallel)	0.2	%	ISO 294–4
MECHANICAL PROPERTIES	VALUE		
Tensile modulus	12000	MPa	ISO 527–1/–2
Stress at break	125	MPa	ISO 527–1/–2
Strain at break	1.6	%	ISO 527–1/–2
Flexural modulus	12000	MPa	ISO 178
Flexural strength	180	MPa	ISO 178
Flexural strain at flexural strength	1.8	%	ISO 178–A
Izod impact strength (+23°C)	35	kJ/m ²	ISO 180/1U
THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	260	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	250	°C	ISO 75–1/–2
Burning Behav. at 0.75 mm nom. thickn.	HB	class	IEC 60695–11–10
Thickness tested	0.75	mm	IEC 60695–11–10
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695–11–10

Property Data

Pocan[®] ECOT7142

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Thickness tested	1.5	mm	IEC 60695-11-10
Burning Behav. at 3.0 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	750	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.75	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	750	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	1.5	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	0.75	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	1.5	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	775	°C	IEC 60695-2-13
GWIT (Thickness (3) tested)	3	mm	IEC 60695-2-13

OTHER PROPERTIES	VALUE		
Density	1680	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4-8	h	
Residual moisture content	0.00-0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260-280	°C	
Mold temperature	80-100	°C	