

Pocan[®] T7245

PET—(GF+MX)45

45% Glass/Mineral Reinforced, Injection Molding

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Melt volume—flow rate	35	cm ³ /10min	ISO 1133
Temperature	270	°C	ISO 1133
Load	5	kg	ISO 1133
Molding shrinkage (normal)	1	%	ISO 294–4
Molding shrinkage (parallel)	0.4	%	ISO 294–4
MECHANICAL PROPERTIES	VALUE		
Tensile modulus	12000	MPa	ISO 527–1/–2
Stress at break	115	MPa	ISO 527–1/–2
Strain at break	1.6	%	ISO 527–1/–2
Flexural modulus	11000	MPa	ISO 178
Flexural strength	170	MPa	ISO 178
Flexural strain at flexural strength	2	%	ISO 178–A
Charpy impact strength (+23°C)	30	kJ/m ²	ISO 179/1eU
Izod impact strength (+23°C)	30	kJ/m ²	ISO 180/1U
THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	260	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	180	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	230	°C	ISO 75–1/–2
ELECTRICAL PROPERTIES	VALUE		
Comparative tracking index	225	V	IEC 60112

Property Data

Pocan[®] T7245

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
OTHER PROPERTIES	VALUE		
Density	1820	kg/m³	ISO 1183
PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4–8	h	
Residual moisture content	0.00–0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260–280	°C	
Mold temperature	80–100	°C	