

Pocan[®] TFN4230

(PBT+PET)—GF25 FR(40)

25% Glass Reinforced, Injection Molding, Flame Retardant (halogen free)

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Molding shrinkage (normal)	0.9	%	ISO 294-4
Molding shrinkage (parallel)	0.4	%	ISO 294-4
MECHANICAL PROPERTIES	VALUE		
Tensile modulus	10300	MPa	ISO 527-1/-2
Stress at break	100	MPa	ISO 527-1/-2
Strain at break	1.8	%	ISO 527-1/-2
Flexural modulus	10400	MPa	ISO 178
Flexural strength	160	MPa	ISO 178
Flexural strain at flexural strength	1.8	%	ISO 178-A
Charpy impact strength (+23°C)	30	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	25	kJ/m ²	ISO 179/1eU
Izod impact strength (+23°C)	27	kJ/m ²	ISO 180/1U
THERMAL PROPERTIES	VALUE		
Temp. of deflection under load (1.80 MPa)	200	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.9	E-4/°C	ISO 11359-1/-2
Burning Behav. at 0.75 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10

Property Data

Pocan® TFN4230

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Burning Behav. at 3.0 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.75	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	1.5	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	800	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	0.75	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	800	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	1.5	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	825	°C	IEC 60695-2-13
GWIT (Thickness (3) tested)	3	mm	IEC 60695-2-13

ELECTRICAL PROPERTIES	VALUE		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	42	kV/mm	IEC 60243-1
Comparative tracking index	475	V	IEC 60112
Comparative tracking index (PLC)	1	class	UL 746A

OTHER PROPERTIES	VALUE		
Density	1580	kg/m³	ISO 1183

PROCESSING RECOMMENDATIONS	VALUE		
Drying temperature circulating air dryer	120	°C	
Drying time circulating air dryer	4-8	h	
Residual moisture content	0.00-0.02	%	acc. to Karl Fischer
Melt temperature (Tmin – Tmax)	260-270	°C	

Property Data

Pocan[®] TFN4230

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Mold temperature	80–100	°C	
admissible residence time at Tmax	<5	min	