

Xytron™ G4020T

PPS–GF40

40% Glass Reinforced, Flame Retardant

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	VALUE		
Molding shrinkage (parallel)	0.2	%	ISO 294–4
Molding shrinkage (normal)	0.5	%	ISO 294–4
MECHANICAL PROPERTIES			
	VALUE		
Tensile modulus	15000	MPa	ISO 527–1/–2
Tensile modulus (120°C)	6700	MPa	ISO 527–1/–2
Tensile modulus (160°C)	5300	MPa	ISO 527–1/–2
Tensile modulus (200°C)	4100	MPa	ISO 527–1/–2
Stress at break	200	MPa	ISO 527–1/–2
Stress at break (120°C)	85	MPa	ISO 527–1/–2
Stress at break (160°C)	65	MPa	ISO 527–1/–2
Stress at break (200°C)	50	MPa	ISO 527–1/–2
Strain at break	2	%	ISO 527–1/–2
Strain at break (120°C)	4.1	%	ISO 527–1/–2
Strain at break (160°C)	3.8	%	ISO 527–1/–2
Strain at break (200°C)	3.9	%	ISO 527–1/–2
Flexural modulus	14000	MPa	ISO 178
Flexural strength	280	MPa	ISO 178
Flexural modulus (120°C)	8200	MPa	ISO 178
Flexural modulus (160°C)	5000	MPa	ISO 178
Flexural modulus (200°C)	4300	MPa	ISO 178
Charpy impact strength (+23°C)	60	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	62	kJ/m²	ISO 179/1eU

Xytron™ G4020T

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Charpy notched impact strength (+23°C)	10.5	kJ/m²	ISO 179/1eA
Charpy notched impact strength (−30°C)	11	kJ/m²	ISO 179/1eA

THERMAL PROPERTIES	VALUE		
Melting temperature (10°C/min)	280	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	265	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.15	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.4	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, parallel, above Tg	0.15	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, normal, above Tg	1.1	E-4/°C	ISO 11359-1/-2
Burning Behav. at 3.0 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	3	mm	IEC 60695-11-10
UL recognition	Yes	–	–
Relative Temperature Index – electrical	130	°C	UL746B
RTI electrical (Thickness (1) tested)	0.4	mm	UL746B

ELECTRICAL PROPERTIES	VALUE		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	22	kV/mm	IEC 60243-1
Comparative tracking index	150	V	IEC 60112
Dissipation factor (5GHz)	55	E-4	IEC 61189-2-721
Relative permittivity (5GHz)	4	–	IEC 61189-2-721

OTHER PROPERTIES	VALUE		
Density	1650	kg/m³	ISO 1183
Humidity absorption	0.04	%	Sim. to ISO 62