

Arnitel[®] ECO L400

TPC

>50% Renewable Content, Food Contact Quality

Sustainability

Bio-based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume-flow rate	45	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (parallel)	1.2	%	ISO 294-4
Molding shrinkage (normal)	1.2	%	ISO 294-4
MECHANICAL PROPERTIES		VALUE	
Shore D Hardness (3s)	34	—	ISO 868
Tensile modulus	40	MPa	ISO 527-1/-2
Stress at break	9	MPa	ISO 527-1/-2
Nominal strain at break	200	%	ISO 527-1/-2
Stress at 5% strain	2.7	MPa	ISO 527-1/-2
Stress at 10% strain	4.5	MPa	ISO 527-1/-2
Stress at 50% strain	7.7	MPa	ISO 527-1/-2
Stress at 100% strain	8.3	MPa	ISO 527-1/-2
Tear strength	75	kN/m	ISO 34-1; Method B
Compression Set under constant strain at 70 °C	47	%	ISO 815

THERMAL PROPERTIES

VALUE

Arnitel[®] ECO L400

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Melting temperature (10°C/min)	158	°C	ISO 11357-1/-3
ELECTRICAL PROPERTIES	VALUE		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	20	kV/mm	IEC 60243-1
OTHER PROPERTIES	VALUE		
Density	1100	kg/m³	ISO 1183
Humidity absorption	0.04	%	Sim. to ISO 62