



Telcar® 95-T0769V-90NT

Teknor Apex Company - Ethylene Vinyl Acetate Copolymer

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.920		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	750	psi	ASTM D638
Tensile Strength (Break)	1420	psi	ASTM D638
Tensile Elongation (Break)	750	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	90		ASTM D2240

Notes

¹ Typical properties: these are not to be construed as specifications.