



Sinpolene FRN1982

Teknor Apex Asia Pacific PTE. LTD. - Low Density Polyethylene

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Asia Pacific	• Latin America
Additive	• Flame Retardant		
Features	• Flame Retardant		
Uses	• Film	• Thin-walled Parts	
Appearance	• Natural Color		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.50		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	60	g/10 min	ASTM D1238
Flammability	Nominal Value	Unit	Test Method
Flame Rating	VTM-2		UL 94

Additional Information

Suitable for use in PE
Recommended Dosage: 10%

Notes

¹ Typical properties: these are not to be construed as specifications.