



Chemlon® 250 GHA

Teknor Apex Company - Polyamide 6

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	32600	psi	ISO 527
Tensile Strain (Break)	3.0	%	ISO 527
Flexural Modulus	1.89E+6	psi	ISO 178/A
Flexural Stress	42100	psi	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (73°F)	6.2	ft-lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	> 392	°F	ISO 75-2/A
Melting Temperature	428	°F	ISO 11357
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.031 in)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.