



Chemlon® 60GS3

Teknor Apex Company (Chem Polymer) - Polyamide 6

General Information

Product Description

60GS3 is a 15% glass sphere filled nylon 6.

General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Bead, 15% Filler by Weight
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.24	--	g/cm ³	ISO 1183
Molding Shrinkage ²	1.2 to 1.6	--	%	Internal Method
Water Absorption Equilibrium, 73°F, 50% RH	2.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	435000	232000	psi	ISO 527-2
Tensile Stress	10200	5800	psi	ISO 527-2
Tensile Strain (Break)	10	--	%	ISO 527-2
Flexural Modulus	319000	102000	psi	ISO 178
Flexural Stress	13100	6530	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	3.3	7.6	ft-lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength	24 ft-lb/in ²	No Break		ISO 179/1eU
Notched Izod Impact Strength	2.4	--	ft-lb/in ²	ISO 180/A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature 66 psi, Unannealed	374	--	°F	ISO 75-2/B
Heat Deflection Temperature 264 psi, Unannealed	140	--	°F	ISO 75-2/A
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+11	ohms	IEC 60093
Volume Resistivity	1.0E+16	1.0E+14	ohms·cm	IEC 60093
Electric Strength (0.118 in)	250	200	V/mil	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating 0.06 in, Teknor Apex test result	HB	--		UL 94

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	20	hr
Rear Temperature	446 to 536	°F
Middle Temperature	446 to 536	°F
Front Temperature	446 to 536	°F
Processing (Melt) Temp	464 to 518	°F

Chemlon® 60GS3

Teknor Apex Company (Chem Polymer) - Polyamide 6

Injection	Dry Unit
Mold Temperature	140 to 176 °F
Injection Rate	Fast
Back Pressure	Low
Screw Speed	Moderate

Injection Notes

No drying is necessary unless the material has been exposed to air for longer than three hours. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present.

Notes

¹ Typical properties: these are not to be construed as specifications.

² Mould shrinkage is significantly influenced by many factors including wall thickness, gating, moulding shape and processing conditions. The range values given are determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).