



# Chemlon® 60GS6

Teknor Apex Company - Polyamide 6

## General Information

### Product Description

60GS6 is a 30% glass sphere filled nylon 6.

### General

|                        |                                    |
|------------------------|------------------------------------|
| Material Status        | • Commercial: Active               |
| Availability           | • Europe • North America           |
| Filler / Reinforcement | • Glass Bead, 30% Filler by Weight |
| Forms                  | • Pellets                          |
| Processing Method      | • Injection Molding                |

## ASTM & ISO Properties <sup>1</sup>

| Physical                          | Dry                      | Conditioned | Unit                  | Test Method     |
|-----------------------------------|--------------------------|-------------|-----------------------|-----------------|
| Density                           | 1.35                     | --          | g/cm <sup>3</sup>     | ISO 1183        |
| Molding Shrinkage <sup>2</sup>    | 0.60 to 1.5              | --          | %                     | Internal Method |
| Water Absorption                  |                          |             |                       | ISO 62          |
| Equilibrium, 73°F, 50% RH         | 2.0                      | --          | %                     |                 |
| Mechanical                        | Dry                      | Conditioned | Unit                  | Test Method     |
| Tensile Modulus                   | 508000                   | 247000      | psi                   | ISO 527-1       |
| Tensile Stress (Break)            | 11600                    | 5800        | psi                   | ISO 527-2       |
| Tensile Strain (Break)            | 10                       | 20 to 50    | %                     | ISO 527-2       |
| Flexural Modulus                  | 363000                   | 145000      | psi                   | ISO 178         |
| Flexural Stress                   |                          |             |                       | ISO 178         |
| -- <sup>3</sup>                   | 18100                    | --          | psi                   |                 |
| -- <sup>4</sup>                   | --                       | 8700        | psi                   |                 |
| Impact                            | Dry                      | Conditioned | Unit                  | Test Method     |
| Charpy Notched Impact Strength    | 3.1                      | 5.7         | ft-lb/in <sup>2</sup> | ISO 179         |
| Charpy Unnotched Impact Strength  | 18 ft-lb/in <sup>2</sup> | No Break    |                       | ISO 179         |
| Notched Izod Impact Strength      | 1.9                      | --          | ft-lb/in <sup>2</sup> | ISO 180         |
| Thermal                           | Dry                      | Conditioned | Unit                  | Test Method     |
| Deflection Temperature Under Load |                          |             |                       | ISO 75-2/B      |
| 66 psi, Unannealed                | 401                      | 365         | °F                    |                 |
| Deflection Temperature Under Load |                          |             |                       | ISO 75-2/A      |
| 264 psi, Unannealed               | 158                      | 149         | °F                    |                 |
| Electrical                        | Dry                      | Conditioned | Unit                  | Test Method     |
| Surface Resistivity               | 1.0E+14                  | 1.0E+11     | ohms                  | IEC 60093       |
| Volume Resistivity                | 1.0E+16                  | 1.0E+14     | ohms-cm               | IEC 60093       |
| Electric Strength (0.118 in)      | 280                      | 200         | V/mil                 | IEC 60243-1     |
| Relative Permittivity             | 3.80                     | 4.20        |                       | IEC 60250       |
| Comparative Tracking Index        | 600                      | 500         | V                     | IEC 60112       |
| Flammability                      | Dry                      | Conditioned | Unit                  | Test Method     |
| Flame Rating                      |                          |             |                       | UL 94           |
| 0.06 in, Teknor Apex test result  | HB                       | --          |                       |                 |
| Oxygen Index                      | 24                       | --          | %                     | ISO 4589-2      |

# Chemlon® 60GS6

## Teknor Apex Company - Polyamide 6

### Processing Information

| Injection              | Dry        | Unit |
|------------------------|------------|------|
| Drying Temperature     | 176        | °F   |
| Drying Time            | 2.0        | hr   |
| Rear Temperature       | 446 to 536 | °F   |
| Middle Temperature     | 446 to 536 | °F   |
| Front Temperature      | 446 to 536 | °F   |
| Processing (Melt) Temp | < 572      | °F   |
| Mold Temperature       | 140 to 176 | °F   |
| Injection Rate         | Fast       |      |
| Screw Speed            | 50 to 200  | rpm  |

### Injection Notes

Drying is necessary if material has been exposed to air for longer than 3 hours.

Back pressure: Low

Injection pressure: High

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Mould shrinkage is significantly influenced by many factors including wall thickness, gating, moulding shape and processing conditions. The range values given are determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).

<sup>3</sup> Break

<sup>4</sup> Yield