



Chemlon® 113 G

Teknor Apex Company - Polyamide 66

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 13% Filler by Weight
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.40 to 0.70	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	16500	psi	ISO 527
Tensile Strain (Break)	3.0	%	ISO 527
Flexural Modulus	674000	psi	ISO 178/A
Flexural Stress	24700	psi	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (73°F)	> 1.4	ft·lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	419	°F	ISO 75-2/A
Melting Temperature	495	°F	DSC
RTI Elec			UL 746B
0.03 in	239	°F	
0.06 in	239	°F	
0.12 in	239	°F	
RTI Imp			UL 746B
0.03 in	167	°F	
0.06 in	167	°F	
0.12 in	185	°F	
RTI Str			UL 746B
0.03 in	203	°F	
0.06 in	203	°F	
0.12 in	203	°F	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (0.118 in)	460	V/mil	ASTM D149
Comparative Tracking Index (CTI)	600	V	UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.03 in)	HB		UL 94
Oxygen Index	25	%	ASTM D2863
FMVSS Flammability	PASSES		FMVSS 302

Chemlon® 113 G

Teknor Apex Company - Polyamide 66

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	175	°F
Suggested Max Moisture	0.20	%
Suggested Max Regrind	25	%
Rear Temperature	465 to 490	°F
Middle Temperature	495 to 525	°F
Front Temperature	505 to 540	°F
Nozzle Temperature	505 to 535	°F
Processing (Melt) Temp	505 to 535	°F

Notes

¹ Typical properties: these are not to be construed as specifications.