



Chemlon® 133 GVH

Teknor Apex Company - Polyamide 66

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.59	g/cm ³	ISO 1183
Molding Shrinkage	0.15 to 0.30	%	ISO 2577
Water Absorption (24 hr, 73°F)	0.60	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	19600	psi	ISO 527
Tensile Strain (Break)	2.0	%	ISO 527
Flexural Modulus	1.30E+6	psi	ISO 178/A
Flexural Stress	27600	psi	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (73°F)	> 2.9	ft-lb/in ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	469	°F	ISO 75-2/A
Melting Temperature	495	°F	DSC
CLTE - Flow	2.8E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+18	ohms·cm	ASTM D257
Dielectric Strength (0.118 in)	380	V/mil	ASTM D149
Comparative Tracking Index (CTI)	300	V	UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.03 in)	V-0		UL 94
Oxygen Index	33	%	ASTM D2863
FMVSS Flammability	PASSES		FMVSS 302

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	175	°F
Suggested Max Moisture	0.20	%
Suggested Max Regrind	25	%
Rear Temperature	465 to 495	°F
Middle Temperature	505 to 535	°F
Front Temperature	505 to 545	°F
Nozzle Temperature	505 to 545	°F
Processing (Melt) Temp	505 to 545	°F

Notes

¹ Typical properties: these are not to be construed as specifications.