



Chemlon® 135 MA

Teknor Apex Company - Polyamide 66

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Magnetite		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F)	0.70	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	551000	psi	ISO 527
Tensile Stress	10200	psi	ISO 527
Tensile Strain (Break)	8.0	%	ISO 527
Flexural Modulus	464000	psi	ISO 178/A
Flexural Stress	13100	psi	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (73°F)	2.9	ft-lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	500	°F	ISO 11357

Notes

¹ Typical properties: these are not to be construed as specifications.