



Chemlon® 150 GHU

Teknor Apex Company - Polyamide 66

General Information

Product Description

Chemlon® 150 GHU is a 50% glass fiber reinforced, heat and UV stabilized polyamide 66 (PA 66) designed for injection molding; primarily in metal replacement. This high tensile strength material has a wide processing window, provides a good surface appearance, and is available globally.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Heat Stabilizer	• UV Stabilizer	
Features	• Good Processability • Good Surface Finish	• Good Thermal Stability • High Tensile Strength	• UV Resistant
RoHS Compliance	• Contact Manufacturer		
Automotive Specifications	• STELLANTIS MS-DB-41 ¹		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ²

Physical	Dry	Conditioned	Unit	Test Method
Density	1.58	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.2	--	%	
Flow	0.13	--	%	
Water Absorption (24 hr, 73°F)	0.60	--	%	ISO 62
Water Absorption				ISO 62
Saturation, 73°F	1.4	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2.98E+6	2.11E+6	psi	ISO 527
Tensile Stress	34800	24700	psi	ISO 527
Tensile Strain (Break)	2.5	4.1	%	ISO 527
Flexural Modulus	2.18E+6	1.72E+6	psi	ISO 178
Flexural Stress	40600	36100	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	4.8	7.1	ft·lb/in ²	ISO 179
Charpy Unnotched Impact Strength	33	34	ft·lb/in ²	ISO 179
Notched Izod Impact Strength	4.8	7.1	ft·lb/in ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/B
66 psi, Unannealed	487	--	°F	
Deflection Temperature Under Load				ISO 75-2/A
264 psi, Unannealed	> 482	--	°F	
Melting Temperature	482	--	°F	ASTM D789
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.03 in)	HB	--		UL 94

Chemlon® 150 GHU

Teknor Apex Company - Polyamide 66

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Suggested Max Moisture	0.10	%
Processing (Melt) Temp	509 to 559	°F
Mold Temperature	171 to 190	°F

Injection Notes

Maximum peak injection pressure should not exceed 80% of the machine's maximum pressure capability. Start with a holding pressure that is half the peak injection pressure. Perform a rheology curve in order to determine appropriate injection rate.

Notes

¹ Automotive site approvals apply for US manufactured compound only

² Typical properties: these are not to be construed as specifications.