



Chemlon® 182

Teknor Apex Company - Polyamide 66

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• Flame Retardant		
Features	• Flame Retardant		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Molding Shrinkage	0.90 to 1.4	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	10600	psi	ISO 527
Tensile Strain (Break)	7.0	%	ISO 527
Flexural Modulus	466000	psi	ISO 178/A
Flexural Stress	15200	psi	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (73°F)	> 1.4	ft-lb/in ²	ISO 180/A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	437	°F	ISO 75-2/B
Deflection Temperature Under Load 264 psi, Unannealed	230	°F	ISO 75-2/A
Melting Temperature	495	°F	DSC
RTI Elec			UL 746B
0.03 in	248	°F	
0.06 in	248	°F	
0.12 in	248	°F	
RTI Imp			UL 746B
0.03 in	203	°F	
0.06 in	221	°F	
0.12 in	221	°F	
RTI Str			UL 746B
0.03 in	248	°F	
0.06 in	248	°F	
0.12 in	248	°F	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (0.118 in)	430	V/mil	ASTM D149
Comparative Tracking Index (CTI)	600	V	UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.022 in)	V-0		UL 94
Oxygen Index	33	%	ASTM D2863

Chemlon® 182

Teknor Apex Company - Polyamide 66

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	175	°F
Suggested Max Moisture	0.20	%
Rear Temperature	475 to 495	°F
Middle Temperature	505 to 515	°F
Front Temperature	505 to 525	°F
Nozzle Temperature	515 to 535	°F
Processing (Melt) Temp	505 to 530	°F

Notes

¹ Typical properties: these are not to be construed as specifications.