



PTS- Creamid A3H7.5G10*9000

Teknor Apex Company (Chem Polymer) - Polyamide 66

General Information

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.58	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.90	%	
Flow	0.30	%	
Water Absorption (24 hr, 73°F)	0.40	%	ISO 62
Water Absorption (Saturation, 73°F)	3.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2.47E+6	psi	ISO 527-2
Tensile Stress (Break)	35500	psi	ISO 527-2
Tensile Strain (Break)	3.1	%	ISO 527-2
Flexural Modulus (73°F)	2.13E+6	psi	ISO 178
Flexural Stress	46400	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	5.7	ft-lb/in ²	ISO 179
Charpy Unnotched Impact Strength (73°F)	38	ft-lb/in ²	ISO 179
Notched Izod Impact Strength (73°F)	6.2	ft-lb/in ²	ISO 180

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 4.0	hr
Nozzle Temperature	554	°F
Processing (Melt) Temp	536 to 572	°F
Mold Temperature	176 to 230	°F

Notes

¹ Typical properties: these are not to be construed as specifications.